

Technical Date Sheet

Model Code: A40

Properties		Normal Standards
Hardness(Shore A)		38 – 42
A&B Mixing Ratio(by weight)		1 – 1
Viscosity(m P a ·s)	Part A	3000 – 5000
	Part B	3000 – 5000
	Mixture	3000 – 5000
Working Time(mins,25°C)		40- 60mins
Curing Time(Hrs,25°C)		4 – 6 hrs
Cured-Tear Strength(kN/m)		12 – 16
Cured-Tensile Strength(MPa)		6.0 – 8.0
Elongation(%)		350-500%
Shrinkage(%)		</= 0.1%

Tel: 09133086110 – 09131665475

Website: <https://khodaei-machinery.com/>

Email: info@khodaei-machinery.com